



**GAIL (India) Ltd.**  
(A Govt. of India Undertaking)  
Petrochemicals Marketing

## I62A080U

High Density Polyethylene for Injection Moulding

### Product Description and Typical Applications:

I62A080U has excellent processability with optimum balance of mechanical properties, dimensional stability and gloss. It is used for general purpose crates etc.

Property	Values*	Unit	Test Method
Melt Flow Index (I <sub>2</sub> )	8.2	gm/10min	ASTM D1238
Density	0.963	gm/cc	ASTM D1505
Tensile Strength @Yield	310	kg/cm <sup>2</sup>	ASTM D638
Elongation @ Yield	7	%	ASTM D638
Flexural Modulus	14000	kg/cm <sup>2</sup>	ASTM D790
Vicat Softening Temperature	128	°C	ASTM D1525

\* Typical characteristics of the product given purely as a guide. Molded and tested in accordance with ASTM D4976

### Processing Guidelines:

Barrel temperature: 200 - 280°C

Mould temperature: 30-40°C

### Regulatory Information:

Certificate is available on request.

### Packaging & Storage:

I62A080U is available in natural colour/pellet form in 25 kg strong bags made of woven fabric. The product should be stored in dry conditions at temperature below 50°C and protected from UV light.

*For any technical assistance contact:*

**GAIL Polymer Technology Centre, GAIL (India) Limited**

PARC Building, Plot No. 24, Sector-16A, Noida, (U.P.) India – 201301

Ph.: 0120-2515353/354/355/363 Fax No.: 0120-2511134, Website: [www.gailonline.com](http://www.gailonline.com)

The information, data and suggestions contained herein are to the best of our knowledge accurate and reliable. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user specific application.