Provisional Technical Datasheet





High Density Polyethylene

Injection Molding

Product Description:

Typical Properties:

HDPE M5618 is a natural colored grade produced with the latest Mitsui CX slurry polymerization Technology exhibiting following features:

- ✓ High flow for Good Processability
- ✓ Good Rigidity

HDPE M5618 is recommended for following applications:

- ✓ Housewares, Baskets
- ✓ Buckets, Tubs
- ✓ Caps & Closures
- ✓ Thin wall drinking glass/cups

| Sr. No. | Properties | Test Method | Units | Values* |
|---------|---|-------------|--------------------|---------|
| Physica | I Properties | | | |
| 1 | Melt Flow Index (190°C & 2.16 kg) | ASTM D1238 | g / 10 min | 18 |
| 2 | Density (at 23 ⁰ C) | ASTM D1505 | gm/cm ³ | 0.956 |
| Mechan | ical Properties | - | • | |
| 3 | Tensile Strength @ Yield (50mm / min) | ASTM D638 | MPa | 24.0 |
| 4 | Elongation @ Break (50mm / min) | ASTM D638 | % | 350 |
| 5 | Flexural Modulus | ASTM D790 | Мра | 850 |
| 6 | Izod Impact Strength (at 23 ⁰ C) | ASTM D256 | J/m | 35 |
| 7 | Hardness | ASTM D2240 | Shore D | 65 |
| Therma | Properties | | - | |
| 8 | Vicat Softening Point (10N) | ASTM D1525 | °C | 122 |
| 9 | Heat Deflection Temperature (0.455 MPa) | ASTM D648 | °C | 78 |

* Typical Values and not to be taken as specification limits, values may change without any prior notice.

Recommended Processing Temperature: 190 – 230 °C

Disclaimer: OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat,India Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: <u>www.opalindia.in</u> PARC/2016/03 - 00

Provisional Technical Datasheet





Regulatory Requirements:

HDPE grade M5618 shall meet the requirements stipulated in IS 10146:1982 on 'Specification of Polyethylene for safe use in contact with Foodstuff, Pharmaceutical & Drinking water'. The grade and Additives incorporated in this grade shall meet the positive list of constituents as prescribed in IS 10141:1982. The Grade and the additives incorporated in it shall also comply with the FDA: CFR Title 21,177.1520, Olefin Polymers.

Storage & Handling:

Prevent Polyethylene Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the Storage temperature should not exceed 50 °C. Non - compliance to these precautionary measures can lead to degradation of the product causing Color changes, Odor & inadequate product performance.

Health and Safety Information:

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at **www.opalindia.in**. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.



ONGC Petro additions Ltd

Disclaimer: OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat,India Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: <u>www.opalindia.in</u> PARC/2016/03 - 00