## **Technical Data Sheet**

# Moplen HP401H

Polypropylene, Homopolymer

#### **Product Description**

LyondellBasell Australia's polypropylene grade *Moplen* HP401H is a low flow homopolymer with a conventional molecular weight distribution and is formulated with a general purpose additive package. *Moplen* HP401H is designed principally for the production of sheet for subsequent forming operations into packaging containers.

lyondellbasell

### **Regulatory Status**

For regulatory compliance information, see *Moplen* HP401H <u>Product Stewardship Bulletin (PSB) and Safety</u> <u>Data Sheet (SDS)</u>.

| Status            | Commercial: Active  |
|-------------------|---|
| Availability      | Asia-Pacific; Australia and New Zealand                     |
| Application       | Thermoformed Food Containers                                |
| Market            | Industrial Packaging; Rigid Packaging                       |
| Processing Method | Extrusion Blow Molding; Thermoforming                       |
| Attribute         | Good Impact Resistance; Good Processability; Good Stiffness |

|   | Nominal |          | Test Method   |
|---|---------|----------|---------------|
| Typical Properties                                    | Value   | Units    |               |
| Physical  |         |          |               |
| Melt Flow Rate, (230 °C/2.16 kg)                      | 2.2     | g/10 min | ISO 1133-1    |
| Density, (23 °C, Method D)                            | 0.90    | g/cm³    | ISO 1183-1    |
| Mechanical  |         |          |               |
| Flexural Modulus                                      | 1450    | MPa      | ISO 178       |
| Tensile Stress at Yield                               | 33      | MPa      | ISO 527-1, -2 |
| Impact  |         |          |               |
| Notched Izod Impact Strength, (23 °C)                 | 6.0     | kJ/m²    | ISO 180/1A    |
| Hardness  |         |          |               |
| Shore Hardness, (Shore D)                             | 74      |          | ISO 868       |
| Thermal   |         |          |               |
| Vicat Softening Temperature                           | 155     | °C       | ISO 306       |
| Heat Deflection Temperature B, (0.45 MPa, Unannealed) | 91      | °C       | ISO 75B-1, -2 |
|   |         |          |               |

## Notes

These are typical property values not to be construed as specification limits.

#### **Company Information**

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

#### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

#### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.