

# MI100N



## Polypropylene Impact Co Polymer

## Injection Molding & Compounding

### Product Description:

PP Block Co polymer MI100N is a heterophasic natural colored & nucleated grade produced with the latest Ineos Gas Phase polymerization Technology exhibiting following features:

- ✓ Higher flow for easy processing
- ✓ Good Impact – Stiffness balance
- ✓ Anti-static properties

PP Block Co Polymer MI100N is recommended for Injection molding applications such as:

- ✓ Thin wall Injection Molding
- ✓ Stadium Cups
- ✓ Refrigerated Dairy containers
- ✓ High Speed Injection Molding
- ✓ Compounding

### Typical Properties:

Sr. No.	Properties	Test Method	Units	Values*
<b>Physical Properties</b>				
1	Melt Flow Index ( 230°C & 2.16 kg)	ASTM D1238	g / 10 min	100
2	Density (23 °C)	ASTM D 1505	Gm/cm <sup>3</sup>	0.90
<b>Mechanical Properties</b>				
3	Tensile Strength @ Yield (50mm / min)	ASTM D 638	MPa	25
4	Elongation @ Break (50mm / min)	ASTM D 638	%	7
5	Flexural Modulus (1.3 mm/min)	ASTM D790A	MPa	1600
6	Notch Izod Impact Strength ( @ 23°C)	ASTM D 256	J/m	70
7	Hardness (Rockwell)	ASTM D 785	R Scale	90
<b>Thermal Properties</b>				
8	Heat Deflection Temperature (0.46N/m <sup>2</sup> )	ASTM D648	°C	115
* Mechanical Properties tested on Injection molded specimen prepared in accordance with ASTM D 4101 and conditioned as per ASTM D 618				
* Typical Values and not to be taken as specifications, values may change without any prior notice.				

**Recommended Processing Temperature: 180 – 220 °C**

**Disclaimer:** OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall be attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat, India  
Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: [www.opalindia.in](http://www.opalindia.in) PARC/2016/03 - 00

# MI100N



## **Regulatory Requirements:**

PP Co Polymer grade MI100N shall meet the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water'. The grade and Additives incorporated in this grade shall meet the positive list of constituents as prescribed in IS 10909. The Grade and the additives incorporated in it will also comply with the FDA: CFR Title 21,177.1520, Olefin Polymers.

## **Storage & Handling:**

Prevent PP Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the Storage temperature should not exceed 50 °C. Non - compliance to these precautionary measures can lead to degradation of the product causing Color changes, Odor & inadequate product performance.

## **Health and Safety Information:**

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at [www.opalindia.in](http://www.opalindia.in). Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.



## **ONGC Petro additions Ltd**

**Disclaimer:** OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: **ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat,India**  
Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: [www.opalindia.in](http://www.opalindia.in) PARC/2016/03 - 00