

Technical Data Sheet

Lupolen 4261AG

High Density Polyethylene



Product Description

Lupolen 4261AG is a high molecular weight high density polyethylene. Typical customer applications include automotive fuel tanks. It is supplied in pellets and is stabilized with antioxidants for the extrusion process. The product features an outstanding Environmental Stress Cracking Resistance (ESCR), good chemical resistance in combination with an excellent low temperature impact resistance. Typical processes include blow molding and thermoforming.

Lupolen 4261AG is not intended for use in medical and pharmaceutical applications. The product can not be used for food contact applications.

Regulatory Status

For regulatory compliance information, see Lupolen 4261AG [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Fuel Tanks; Non-fuel Reservoirs
Market	Automotive
Processing Method	Extrusion Blow Molding; Thermoforming
Attribute	Antioxidant; High ESCR (Environmental Stress Cracking Resistance); High Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/21.6 kg)	6.0	g/10 min	ASTM D1238
Density, (23 °C)	0.945	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1070	MPa	ASTM D790
Tensile Strength at Yield, (50 mm/min) Type IV bar die cut or machined	23.1	MPa	ASTM D638
Tensile Elongation at Break, (50 mm/min) Type IV bar die cut or machined	600	%	ASTM D638
Environmental Stress Crack Resistance, F ₅₀ (100% Igepal®, Cond A)	>2000	hr	ASTM D1693
Processing Parameters			
Melt Temperature	180 - 240	°C	

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.