

Technical Data Sheet

Petrothene LT602901



High Density Polyethylene

Product Description

Petrothene LT602901 is a high density polyethylene sheet extrusion grade with excellent extrusion characteristics and low warpage. The resulting sheet exhibits good stiffness and impact properties. Typical applications include sheet for signage and packaging.

Regulatory Status

For regulatory compliance information, see *Petrothene* LT602901 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	General Sheet Extrusion; Housewares; Structural Parts
Market	Rigid Packaging
Processing Method	Extrusion Blow Molding; Sheet and Profile Extrusion
Attribute	Good Processability

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.30	g/10 min	0.30	g/10 min	ASTM D1238
Density, (23 °C)	0.960	g/cm ³	0.960	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (1% Secant)	225300	psi	1550	MPa	ASTM D790
Tensile Strength at Yield	4390	psi	30.3	MPa	ASTM D638
Tensile Elongation at Break	1400	%	1400	%	ASTM D638
Impact					
Tensile Impact Strength	101	ft-lb/in ²	212	kJ/m ²	ASTM D1822
Thermal					
Vicat Softening Point	261	°F	127	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	167	°F	75	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.