

## Technical Data Sheet

### Petrothene LP540200



High Density Polyethylene

#### Product Description

Petrothene LP540200 is a copolymer resin selected by customers for blown film applications. This resin offers high ESCR, stiffness, excellent appearance and bubble stability. LP540200 is typically used for high strength multi-wall sack liners and barrier sheeting. It is also useful as a blend component for improved stiffness and machinability.

#### Regulatory Status

For regulatory compliance information, see Petrothene LP540200 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Bags & Pouches; Food Packaging Film; Lamination Film; Secondary Packaging; Shrink Film; Wire & Cable
<b>Market</b>	Flexible Packaging; Rigid Packaging; Wire & Cable
<b>Processing Method</b>	Blown Film; Sheet and Profile Extrusion; Wire & Cable
<b>Attribute</b>	General Purpose; High Tensile Strength

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.17	g/10 min	0.17	g/10 min	ASTM D1238
Density, (23 °C)	0.940	g/cm <sup>3</sup>	0.940	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>					
Tensile Strength at Yield	3180	psi	21.9	MPa	ASTM D638
Environmental Stress Crack Resistance, F <sub>50</sub>	>1000	hr	>1000	hr	ASTM D1693
<b>Film</b>					
Dart Drop Impact Strength, F50	70	g	70	g	ASTM D1709
Tensile Strength at Break					
MD	6800	psi	46.9	MPa	ASTM D882
TD	4300	psi	29.6	MPa	ASTM D882
Tensile Strength at Yield					
MD	2800	psi	19.3	MPa	ASTM D882
TD	3300	psi	22.8	MPa	ASTM D882
Tensile Elongation at Break					
MD	510	%	510	%	ASTM D882
TD	680	%	680	%	ASTM D882
Secant Modulus					
MD	82000	psi	565	MPa	ASTM D882
TD	110000	psi	758	MPa	ASTM D882
Elmendorf Tear Strength					
MD	40	g	40	g	ASTM D1922
TD	1150	g	1150	g	ASTM D1922
<b>Hardness</b>					

Shore Hardness, (Shore D)	62	62	ASTM D2240
<b>Thermal</b>			
Vicat Softening Temperature	246 °F	119 °C	ASTM D1525
Low Temperature Brittleness	<-105 °F	<-76 °C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	147 °F	64 °C	ASTM D648

## Notes

Mechanical tensile properties were run on a Type IV specimen.

Data obtained from 2.0 mil film produced on a blown film line with a 60 mil die gap, 2.5:1 BUR, and 410-430 °F (210-220 °C) melt extrusion temperature.

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## General Extrusion Conditions

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.