

## Technical Data Sheet

### *Alathon M6080UV*



High Density Polyethylene

#### Product Description

*Alathon M6080UV* is a narrow molecular weight distribution homopolymer that exhibits enhanced flow characteristics and good balance of stiffness and impact resistance. Typical applications include cases, tote bins, crates and trays. M6080UV contains a UV stabilizer for outdoor applications.

#### Regulatory Status

For regulatory compliance information, see *Alathon M6080UV* Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). To obtain copies of these documents, please contact your LyondellBasell product safety representative.

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Crates; Pallets/Trays/Tote Bins
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	7.9	g/10 min	7.9	g/10 min	ASTM D1238
Density	0.960	g/cm <sup>3</sup>	0.960	g/cm <sup>3</sup>	ASTM D1505
Bulk Density	37-39	lb/ft <sup>3</sup>	593-625	kg/m <sup>3</sup>	ASTM D1895
Spiral Flow	8.6	in	21.8	cm	LYB Method
<b>Mechanical</b>					
Flexural Modulus					
(1% Secant)	190000	psi	1310	MPa	ASTM D790
(2% Secant)	155000	psi	1070	MPa	ASTM D790
Flexural Young's Modulus	205000	psi	1410	MPa	ASTM D790
Tensile Modulus, (1% Secant)	123000	psi	848	MPa	ASTM D638
Tensile Young's Modulus	146000	psi	1010	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	2300	psi	15.9	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4250	psi	29.3	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	380	%	380	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	11	%	11	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength, (23 °C)	1.4	ft-lb/in	75	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
<b>Hardness</b>					
Shore Hardness, (Shore D, max)	70		70		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	264	°F	129	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	176	°F	80	°C	ASTM D648
Melting Temperature	270.9	°F	132.7	°C	ASTM D3418

---

Crystallization Temperature	240.6 °F	115.9 °C	ASTM D3418
-----------------------------	----------	----------	------------

---

## Notes

Conditions of Tensile Stress and Elongation values are: 50 mm/min, Type IV specimen.

Conditions of Flexural Modulus values are: 0.5 inches/min or 12.5 mm/min.

Conditions of Tensile Modulus values are: 50 mm/min, Type I Specimen.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.