

Technical Data Sheet

Alathon L5008HP



High Density Polyethylene

Product Description

Alathon L5008HP is a bimodal, high molecular weight, high density polyethylene resin with excellent processing characteristics. L5008HP is selected by customers for pressure pipe applications including industrial piping, mining, oil & gas gathering, municipal water service lines and sewers.

Regulatory Status

For regulatory compliance information, see *Alathon* L5008HP [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial
Availability	Africa-Middle East; Asia-Pacific
Application	Drinking Water Pipe
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal		Test Method
	Value	Units	
Physical			
Melt Flow Rate			
(230 °C/2.16 kg)	0.07	g/10 min	ISO 1133-1
(190 °C/21.6 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	0.949	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (2% Secant)	972	MPa	ISO 178
Tensile Stress at Break, (23 °C)	34.3	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	24.5	MPa	ISO 527-1, -2
Tensile Elongation at Break, (23 °C)	635	%	ISO 527-1, -2
PENT on Natural Resin, (2.4 MPa, 80 °C)	3200	hr	ASTM F1473
Thermal			
Oxidation Induction Time, (210 °C)	35	min	ISO 11357-6

Notes

Typical Property values were determined on natural L5800HP resin, unless otherwise noted.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.