

Alathon

M5370PX

High Density Polyethylene
Extrusion Grade

Melt Index 6.8 Density 0.953



Applications

Alathon M5370PX is a copolymer with a narrow molecular weight distribution. This resin provides high impact strength and stress crack resistance, excellent color, low odor and good processability. Typical applications include pipe and profile extrusion.

Regulatory Status

M5370PX meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales or technical service representative for more information.

Processing Techniques

Specific recommendations for processing M5370PX can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Value	Units	Test Method
Melt Index	6.8	g/10 min	ASTM D 1238
Density	0.953	g/cc	ASTM D 1505
Tensile Stress @ Break	3,250 (22)	psi (MPa)	ASTM D 638
Tensile Stress @ Yield ¹	4,110 (28)	psi (MPa)	ASTM D 638
Elongation @ Yield ¹	7.3	%	ASTM D 638
1% Secant Modulus ²	181,000 (1,250)	psi (MPa)	ASTM D 790
2% Secant Modulus ²	151,000 (1,040)	psi (MPa)	ASTM D 790
Vicat Softening Point	261 (127)	°F (°C)	ASTM D 1525
Hardness, Shore D	67		ASTM D 2240
Heat Deflection Temperature, 66 psi	162 (72)	°F (°C)	ASTM D 648
Low Temperature Brittleness, F ₅₀	<-105 (<-76)	°F (°C)	ASTM D 746

¹ Crosshead speed: 2"/min

² Crosshead speed: 0.5"/min

Equistar Chemicals, LP, is a member of the LyondellBasell group companies.

Alathon is a trademark owned or used by one of the LyondellBasell family of companies. Trademark *Alathon* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P. O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
www.lyondellbasell.com