

Technical Data Sheet
Hyperzone HY4008



High Density Polyethylene

Product Description

Hyperzone HY4008 is a bimodal, high molecular weight, high density polyethylene resin with excellent processing characteristics. HY4008 is selected by customers for pressure pipe applications including industrial piping, mining, oil & gas gathering, municipal water lines and sewers. *Hyperzone* HY4008 is classified as PE100 and customers typically use HY4008 in applications requiring high resistance to pipe failure by rapid crack propagation and slow crack growth mechanisms.

Regulatory Status

For regulatory compliance information, see *Hyperzone* HY4008 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific
Application	Drinking Water Pipe
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate			
(230 °C/5.0 kg)	0.25	g/10 min	ISO 1133-1
(230 °C/21.6 kg)	7.5	g/10 min	ISO 1133-1
Density, (23 °C)	0.9495	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (1% Secant)	1020	MPa	ISO 178
Tensile Modulus, (23 °C, 50 mm/min, Chord)	1030	MPa	ISO 527-1, -2
Tensile Stress at Break	31	MPa	ISO 527-1, -2
Tensile Stress at Yield	24	MPa	ISO 527-1, -2
Tensile Elongation at Break	620	%	ISO 527-1, -2
Thermal			
Oxidative-Induction Time, (210 °C)	>60	min	ASTM D3895
Conformance Testing			
Minimum Required Strength, (20 °C)	10	MPa	ISO 12162
Creep Rupture Strength, (20 °C, 12.4 MPa)	>500	hr	ISO 1167-1, -2
Resistance to Rapid Crack Propagation, Pc @ 0 °C	>12	bar	ISO 13477
Values were obtained on 12" SDR11 pipe made with HY4008 and an approved masterbatch.			
Resistance to Rapid Crack Propagation, Tc @ 5 bar (12")	<-9	°C	ISO 13477
Values were obtained on 12" SDR11 pipe made with HY4008 and an approved masterbatch.			
Resistance to Rapid Crack Propagation, Tc @ 5 bar (4")	<-21	°C	ISO 13477
Values were obtained on 4" SDR11 pipe made with HY4008 and an approved masterbatch.			

Values were obtained on 4" SDR11 pipe made with HY4008 and an approved masterbatch.

Notes

Typical Property values were determined on natural HY4008 resin, unless otherwise noted. Conformance Test values were determined from HY4008 compounded with an approved masterbatch.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.