### **Technical Data Sheet**

## Alathon L5645

High Density Polyethylene



### **Product Description**

*Alathon* L5645 is a medium molecular weight, high density polyethylene homopolymer for use in blown film applications. Typical applications include general-purpose HDPE film applications such as overwrap, laminating base films, food packaging and oriented tapes.

# **Regulatory Status**

For regulatory compliance information, see *Alathon* L5645 <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

Status Commercial: Active
Availability North America

**Application** Agriculture Film; Bags & Pouches; Nets; Raffia/Tapes/Strapping; Secondary

Packaging

Market Flexible Packaging

Processing Method Blown Film; Tapes & Raffia

Attribute General Purpose; Good Abrasion Resistance; Good Organoleptic Properties; High

Density; High Stiffness; Low Gel

|                                  | Nominal | English  | Nominal | SI       |             |
|----------------------------------|---------|----------|---------|----------|-------------|
| Typical Properties               | Value   | Units    | Value   | Units    | Test Method |
| Physical                         |         |          |         |          |             |
| Melt Flow Rate, (190 °C/2.16 kg) | 0.54    | g/10 min | 0.54    | g/10 min | ASTM D1238  |
| Density, (23 °C)                 | 0.959   | g/cm³    | 0.959   | g/cm³    | ASTM D1505  |
| Film                             |         |          |         |          |             |
| Tensile Strength at Break        |         |          |         |          |             |
| MD                               | 7600    | psi      | 52.4    | MPa      | ASTM D882   |
| TD                               | 3500    | psi      | 24.1    | MPa      | ASTM D882   |
| Tensile Strength at Yield        |         |          |         |          |             |
| MD                               | 4000    | psi      | 27.6    | MPa      | ASTM D882   |
| TD                               | 4600    | psi      | 31.7    | MPa      | ASTM D882   |
| Tensile Elongation at Break      |         |          |         |          |             |
| MD                               | 550     | %        | 550     | %        | ASTM D882   |
| TD                               | 500     | %        | 500     | %        | ASTM D882   |
| Secant Modulus                   |         |          |         |          |             |
| MD                               | 137000  | psi      | 945     | MPa      | ASTM D882   |
| TD                               | 183000  | psi      | 1260    | MPa      | ASTM D882   |
| Elmendorf Tear Strength          |         |          |         |          |             |
| MD                               | 31      | g        | 31      | g        | ASTM D1922  |
| TD                               | 1700    | g        | 1700    | g        | ASTM D1922  |

#### **Notes**

Data obtained from 2.0 mil film produced on a blown film line with a 60 mil die gap, 2.2:1 BUR, and 390-410 °F (199-210 °C) melt extrusion temperature.

These are typical property values not to be construed as specification limits.

# **Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

# **Company Information**

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

#### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

### **Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 2/25/2023