

Hifax EP200R



Polypropylene, Impact Copolymer

Product Description

Moplen EP200R is a "Reactor-made Thermoplastic PolyOlefin", super impact copolymer with high impact resistance. Typical customer application is compounding base resin for automotive bumper fascia.

Regulatory Status

For regulatory compliance information, see Hifax EP200R [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand
Application	Exterior Automotive Applications; Interior Automotive Applications
Market	Automotive; Consumer Products; Industrial Packaging
Processing Method	Injection Molding
Attribute	Good Processability; Good Toughness; Impact Copolymer; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ASTM D1238
Density	0.90	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus	750	MPa	ASTM D790
Tensile Strength at Yield	18	MPa	ASTM D638
Tensile Elongation at Yield	6	%	ASTM D638
Impact			
Notched Izod Impact Strength			
(23 °C)	No Break		ASTM D256
(-20 °C)	130	J/m	ASTM D256
Hardness			
Shore Hardness, (Shore D)	60		ASTM D2240
Rockwell Hardness, (R-Scale)	50		ASTM D785
Thermal			
Vicat Softening Point	130	°C	ASTM D1525
Deflection Temperature Under Load, (0.46 N/mm ²)	85	°C	ASTM D648
Optical			
Gardner Gloss, (60°)	30		ASTM D523

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.