Technical Data Sheet

Hifax EP3080

Polypropylene, Impact Copolymer



Product Description

Hifax EP3080 is non-filled polypropylene copolymer for injection molding with very high impact strength. The grade features improved processability. The grade is natural, in pellet form.

Hifax EP3080 is currently used by customers for the production of painted bumpers for automotive.

Regulatory Status

For regulatory compliance information, see *Hifax* EP3080 <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).</u>

Status Commercial: Active

Availability Africa-Middle East; Europe

Application Bumpers
Market Automotive

Processing Method Compounding; Injection Molding

Attribute High Impact Resistance

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7.5	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.89	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	900	MPa	ISO 178
Tensile Modulus	800	MPa	ISO 527-1, -2
Tensile Stress at Break	15	MPa	ISO 527-1, -2
Tensile Stress at Yield	17	MPa	ISO 527-1, -2
Tensile Strain at Break	500	%	ISO 527-1, -2
Tensile Strain at Yield	6	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	65	kJ/m²	ISO 179
(-20 °C)	15	kJ/m²	ISO 179
(-30 °C)	10	kJ/m²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	130	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2
DSC Melting Point	163	°C	ISO 11357-3

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 10/18/2022