Technical Data Sheet

Hifax TYC 462P C2 C12472

lyondellbasell

Polypropylene, Impact Copolymer

Product Description

Hifax TYC 462P is a 30% talc reinforced, high flow, impact modified and UV stabilized polypropylene copolymer for injection molding. It combines an excellent flowability with good processability and durability and offers excellent esthetic properties for exterior applications. The grade has been specifically designed for molding large complex parts that require good dimensional stability.

Regulatory Status

For regulatory compliance information, see *Hifax* TYC 462P C2 C12472 <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Availability Asia-Pacific

Application Exterior Automotive Applications

Processing Method Injection Molding

Attribute Durable; Good Dimensional Stability; Good Impact Resistance; Good Processability;

Good Stiffness; High Flow; Pleasing Surface Appearance; UV Resistant

Niamalmai

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	32	g/10 min	ISO 1133-1
Density, (23 °C)	1.13	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C)	2000	MPa	ISO 178
Tensile Strength, (23 °C)	18	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	35	kJ/m²	ISO 180/1A
(-30 °C)	3.5	kJ/m²	ISO 180/1A

LyondellBasell Technical Data Sheet Date: 10/18/2022

Notes

These are typical property values not to be construed as specification limits.

Availability indicates the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this
 product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 10/18/2022