Technical Data Sheet

Moplen EP500N

Polypropylene, Impact Copolymer



Product Description

Moplen EP500N is a polypropylene impact copolymer with optimized balance of stiffness and toughness, low warpage, and high impact at low temperature. Typical customer applications are injection molding of crates and pails, electrical appliances parts and general housewares.

Regulatory Status

For regulatory compliance information, see *Moplen* EP500N <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

Status Commercial: Active

AvailabilityAfrica-Middle East; Asia-Pacific; Australia and New ZealandApplicationFurniture; Housewares; Opaque Containers; Small AppliancesMarketConsumer Products; Electrical / Electronics; Rigid Packaging

Processing Method Injection Molding

Attribute Good Impact Resistance; Good Processability; Good Stiffness; Impact Copolymer

	Nominal		Test Method
Typical Properties	Value	Units	
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ASTM D1238
Density	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	1150	MPa	ASTM D790
Tensile Strength at Yield	27	MPa	ASTM D638
Tensile Elongation at Yield	6	%	ASTM D638
Impact			
Notched Izod Impact Strength			
(23 °C)	100	J/m	ASTM D256
(-20 °C)	50	J/m	ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	95		ASTM D785
Thermal			
Deflection Temperature Under Load, (0.46 N/mm²)	110	°C	ASTM D648

LyondellBasell Technical Data Sheet Date: 10/20/2022

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 10/20/2022