

Technical Data Sheet

Moplen EP500V



Polypropylene, Impact Copolymer

Product Description

Moplen EP500V is an ultra high fluidity polypropylene copolymer used for injection moulding applications. The product combines high stiffness with good impact resistance, even at sub-zero temperatures. Moplen EP500V is extensively used for items with long flow paths. It is not intended for medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see Moplen EP500V [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Containers; Housewares; Sports, Leisure & Toys; TWIM Food Containers
Market	Compounding; Consumer Products; Rigid Packaging
Processing Method	Compounding; Injection Molding
Attribute	Good Impact Resistance; Good Stiffness; High Flow; Impact Copolymer; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	100	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	135	cm ³ /10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1100	MPa	ISO 178
Tensile Modulus	1100	MPa	ISO 527-1, -2
Tensile Stress at Yield	24	MPa	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	5.0	kJ/m ²	ISO 179
(0 °C)	3	kJ/m ²	ISO 179
(-20 °C)	2	kJ/m ²	ISO 179
Ductile/Brittle Transition Temperature	-4.3	°C	ISO 6603-2
Hardness			
Ball Indentation Hardness	81	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(A/50 N)	149	°C	ISO 306
(B50)	74	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	93	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.