

## Technical Data Sheet

### Pro-fax SC973



Polypropylene, Impact Copolymer

#### Product Description

Pro-fax SC973 high melt flow, fully formulated impact polypropylene copolymer is available in pellet form. This resin is typically used in thin-wall injection molding applications and offers excellent stiffness.

#### Regulatory Status

For regulatory compliance information, see Pro-fax SC973 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Multi Media Packaging; TWIM Food Containers
<b>Market</b>	Consumer Products; Rigid Packaging
<b>Processing Method</b>	Compounding; Injection Molding
<b>Attribute</b>	Contains Antistat; Good Stiffness; High Flow; Medium Slip; Nucleated

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (230 °C/2.16 kg)	107	g/10 min	107	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm <sup>3</sup>	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	215000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1480	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4100	psi			ASTM D638
(50 mm/min)			28	MPa	ASTM D638
Tensile Elongation at Yield	5	%	5	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength					
(73 °F, Method A)	0.6	ft-lb/in			ASTM D256
(23 °C, Method A)			32	J/m	ASTM D256
<b>Thermal</b>					
Deflection Temperature Under Load					
(66 psi, Unannealed)	240	°F			ASTM D648
(0.45 MPa, Unannealed)			116	°C	ASTM D648

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.