Technical Data Sheet

Moplen HP742U

Polypropylene, Homopolymer



Product Description

LyondellBasell Australia's Polypropylene grade *Moplen* HP742U is a very high flow homopolymer with a modified molecular weight. *Moplen* HP742U has been formulated for use in thin walled packaging containers where rapid cycle times are required together with consistent performance, low organoleptic properties (odour and taint) and a balanced level of mechanical properties.

Regulatory Status

For regulatory compliance information, see *Moplen* HP742U <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).</u>

Status Commercial: Active

Availability Asia-Pacific; Australia and New Zealand

Application Containers; TWIM Food Containers

MarketRigid PackagingProcessing MethodInjection Molding

Attribute Fast Cycle (Production); Good Moldability; High Flow; Homopolymer; Nucleated

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	90	g/10 min	ISO 1133-1
Density, (23 °C, Method D)	0.90	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	1850	MPa	ISO 178
Tensile Stress at Yield	38	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	2.2	kJ/m²	ISO 180/1A
Hardness			
Shore Hardness, (Shore D)	75		ISO 868
Thermal			
Vicat Softening Temperature	150	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	102	°C	ISO 75B-1, -2

LyondellBasell Technical Data Sheet Date: 10/8/2022

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 10/8/2022