# Moplen RP225M

Polypropylene, Random Copolymer

## **Product Description**

*Moplen* RP225M is a controlled rheology medium modified propylene random copolymer for manufacturing high transparent cast films. The product contains slip and anti-block agents. It offers good processability, excellent clarity and gloss and exhibits very good heat weldability. Main applications are packaging of foodstuffs, packaging of stationary, shirts and hosiery. It is also suitable for production of stationary folders *Moplen* RP225M is suitable for food contact.

lyondellbasell

## **Regulatory Status**

For regulatory compliance information, see *Moplen* RP225M <u>Product Stewardship Bulletin (PSB) and Safety</u> <u>Data Sheet (SDS)</u>.

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Food Packaging Film; Stationery Film; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Cast Film
Attribute	Controlled Rheology; Good Processability; High Clarity; High Gloss; Random Copolymer; Unspecified Antiblocking; Unspecified Slip; Weldable

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8.0	g/10 min	ISO 1133-1
Density	0.90	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	700	N/mm²	ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)	26.0	N/mm²	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	23.0	N/mm²	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	600	%	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	14.0	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	10.0	kJ/m²	ISO 179-1/1eA
(0 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	125	°C	ISO 306
Deflection Temperature Under Load, (0.46 N/mm <sup>2</sup> )	60	°C	ISO 75B-1, -2

## Notes

These are typical property values not to be construed as specification limits.

### Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

#### **Company Information**

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

#### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.