

Technical Data Sheet

Moplen RP5007K



Polypropylene, Random Copolymer

Product Description

Moplen RP5007K is a nucleated and very high fluidity polypropylene random copolymer with very high fluidity, excellent clarity in low processing temperature for high productivity, less voids formation in injection molding, and good mechanical property balance. Typical customer applications are DVS casing, houseware, thin wall injection molding (TWIM) articles, transparent containers and boxes for food and non food.

Regulatory Status

For regulatory compliance information, see Moplen RP5007K [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific
Application	Clear Containers; Housewares; Multi Media Packaging
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Good Chemical Resistance; Good Dimensional Stability; Good Impact Resistance; Good Processability; High Clarity; High Flow; Medium Rigidity; Random Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	75	g/10 min	ASTM D1238
Density	0.90	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus	1200	MPa	ASTM D790
Tensile Strength at Yield	30	MPa	ASTM D638
Tensile Elongation at Yield	11	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	45	J/m	ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	93		ASTM D785
Thermal			
Deflection Temperature Under Load	90	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.