Pro-fax RP323M

Polypropylene, Random Copolymer

Product Description

Pro-fax RP323M is a barefoot polypropylene random copolymer available in pellet form. This resin is typically used in cast film packaging applications. Typical properties of cast film made with this resin are excellent clarity and gloss, as well as improved cold temperature impact resistance and broader heat seal range compared to homopolymer polypropylene.

lyondellbasell

Regulatory Status

For regulatory compliance information, see *Pro-fax* RP323M <u>Product Stewardship Bulletin (PSB) and Safety</u> <u>Data Sheet (SDS)</u>.

| Status | Commercial: Active |
|-------------------|---|
| Availability | North America |
| Application | Bags & Pouches; Breathable Film; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Hygiene Film; Peelable Film; Stationery Film; Stretch Wrap Film; Twist Wrap Film |
| Market | Flexible Packaging |
| Processing Method | Cast Film |
| Attribute | Good Heat Seal; Good Processability; Opticals |

| Turnian Dranautian | Nominal | English | Nominal | | Test Method |
|---------------------------------------|---------|----------|---------|----------|-------------|
| Typical Properties | Value | Units | Value | Units | Test Method |
| Physical | | | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 8.0 | g/10 min | 8.0 | g/10 min | ASTM D1238 |
| Density, (23 °C) | 0.90 | g/cm³ | 0.90 | g/cm³ | ASTM D792 |
| Mechanical | | | | | |
| Flexural Modulus | | | | | |
| (0.05 in/min, 1% Secant, Procedure A) | 120000 | psi | | | ASTM D790 |
| (1.3 mm/min, 1% Secant, Procedure A) | | | 830 | MPa | ASTM D790 |
| Tensile Strength at Yield | | | | | |
| (2 in/min) | 3600 | psi | | | ASTM D638 |
| (50 mm/min) | | | 24.8 | MPa | ASTM D638 |
| Tensile Elongation at Yield | 14 | % | 14 | % | ASTM D638 |
| Impact | | | | | |
| Notched Izod Impact Strength | | | | | |
| (73 °F, Method A) | 1.2 | ft-lb/in | | | ASTM D256 |
| (23 °C, Method A) | | | 64 | J/m | ASTM D256 |
| Thermal | | | | | |
| Deflection Temperature Under Load | | | | | |
| (66 psi, Unannealed) | 167 | °F | | | ASTM D648 |
| (0.45 MPa, Unannealed) | | | 75 | °C | ASTM D648 |

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.