DATASHEET

ASTM Property





Grade	FI-150
Product	Polypropylene, Homopolymer

General Information					
Key Features -	 Suitable for inflation PP film products Excellent transparency, slipperiness and film opening property Containing slip and anti-blocking agent 				
Applications (Clothes packaging, food packaging				
ltem	Measuring Method	Unit	Value		

ltem	Measuring Method	Unit	Value		
Physical Properties					
Melt Flow Index (230°C, 2.16kg)	ASTM D1238	g/10min	11.0		
Density	ASTM D792	g/cm³	0.9		
Mechanical Properties					
Tensile Stress (Yield)	ASTM D638	kgf/cm²	350		
Tensile Strain (Break)	ASTM D638	%	>500		
Flexural Modulus	ASTM D790	kgf/cm²	16000		
Rockwell Hardness	ASTM D785	R	100		
Impact Properties					
Izod Impact Strength (notched, 23°C)	ASTM D256	kgf∙cm/cm	3		
Thermal Properties					
Melting Temperature	LC Method	℃	162		
Heat Deflection Temperature (4.6kgf/m²)	ASTM D648	°C	104		
Film Properties					
Haze	ASTM D1003	%	<2.5		

^{1.} Physical Properties : these are not to be construed as specifications

^{2.} Measured on $30\mu\text{m}$ mono-layer CPP film made of LOTTE CHEMICAL's cast film grade

^{3.} ISO 9001, 14001, /TS 16949

^{*} The last update date : 2022/09/21