



# High Density Polyethylene

# Technical Data Sheet (TDS)

## SP4808

## Pipe

### Product Description:

Asrene® SP4808 is an HDPE resin which is supplied in natural pellet form and suitable for pressure pipes, water distribution pipes, subduct conduit, sewerage and industrial pipes requiring high tensile properties, excellent stress cracking resistance and long term hydrostatic strength.

### Product Characteristics:

- High tensile properties
- Excellent stress cracking resistance
- Long term hydrostatic strength
- Low sagging grade
- $\sigma_{LPL}$  @50 years = 10.78 MPa

### Applications:

- PE-100 certified (MRS = 10 MPa)
- Pressure pipes
- Water distribution pipes (portable water certified)
- Subduct conduit, sewerage and industrial pipes

Physical Properties	Test Method*	Unit	Value
Density	ASTM D 1505	g/cm <sup>3</sup>	0.949
Melt Index (190 °C/2.16 kg)	ASTM D 1238	g/10 min	0.06
Melt Index (190 °C/5.0 kg)	ASTM D 1238	g/10 min	0.25
Melt Index (190 °C/21.6 kg)	ASTM D 1238	g/10 min	9.0
Brittleness Temperature	ASTM D 746	°C	< -70
ESCR [10% Igepal, F <sub>50</sub> ]	ASTM D 1693	Hrs	> 1,000
Tensile Strength @Yield	ASTM D 638	MPa	30
Tensile Strength @Break	ASTM D 638	MPa	50
Ultimate Elongation	ASTM D 638	%	> 700
Tensile Impact Strength	ASTM D 1822	kJ/m <sup>2</sup>	550
Flexural Modulus	ASTM D 790	MPa	1,300
Oxidative-Induction Time @200 °C	ASTM D 3895	min	> 80
Viscosity @0.1 sec <sup>-1</sup> , 190 °C	Torque Rheometer	Pa.s	> 100,000

Pipe Properties**	Test Method*	Unit	Value
Hydrostatic Resistance @12.4 MPa, 20 °C**	ISO 1167	Hrs	> 100
Hydrostatic Resistance @12.4 MPa, 20 °C**	ISO 1167	Hrs	> 165
Hydrostatic Resistance @12.4 MPa, 20 °C**	ISO 1167	Hrs	> 1,000
Rapid Crack Propagation (S4 test @0 °C)***	ISO 13477	Bar	> 12
Slow Crack Growth (notch test @80 °C, 9.2 bar)***	ISO 13479	Hrs	> 1,058
Longitudinal Reversion***	ISO 2505 1&2	%	0.63

\*Polyethylene tested per ASTM D 1928

\*\*PE-100, S-5, SDR-11, PN-16, OD-32 mm

\*\*\*PE-100, S-5, SDR-11, PN-16, OD-110 mm

Conversion: 1 MPa = 10.2 kgf/cm<sup>2</sup>  
1 kJ/m<sup>2</sup> = 0.01 kgf.cm/mm<sup>2</sup>

### Recommended Processing Conditions:

Melt Temperature.....180-220 °C

### Product Available Form:

Natural pellet

### Packaging:

25 kg in FFS PE-bag





## High Density Polyethylene

## Technical Data Sheet (TDS)

# SP4808

# Pipe

### Safety:

- The product is not classified as a hazardous material.
- Please refer to our Safety Data Sheet (SDS) for details on various aspects of safety, recovery and disposal of the product.

### Storage:

- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials, food and drink, as this may lead to quality deterioration, which results in odor generation and color changes and can have negative effects on the physical properties of this product.
- Keep packaging tightly closed and sealed until ready for use. Packaging that has been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled packaging. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.
- Please refer to our Safety Data Sheet (SDS) for details on storage and handling of the product.

### Regulatory:

- This material complies with recommendations and statutory regulations regarding packaging materials intended to come in contact with foodstuff, such as:
  - FDA Regulation 21 CFR177.1520
  - Commission Regulation EU No.10/2011
  - BPOM Regulation No.HK 03.1.23.07.11.6664 on 2011
  - Halal Certificate from Indonesian Council of Ulama
  - SNI No. 7808:2012
- Please refer to our Regulatory Data Sheet (RDS) for details on various aspects of regulatory of the product.

### Product Stewardship:

PT. Chandra Asri Petrochemical, Tbk. (CAP) has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health and environmental information on our products and then take appropriate steps to protect employee, public health and environment. The success of our Product Stewardship program rests with each and every individual involved with CAP products –from the initial concept and research, to manufacture, storage, sale, use and disposal of each product.

### Disclaimer:

The nominal properties reported herein are typical on the product of CAP but do not reflect normal testing variance and therefore should not to be construed as specifications.

CAP reserves the right to make any improvement or amendments to the composition of any grade or product without alteration to the product code.

This document reports accurate and reliable information to the best of our knowledge on the products manufactured by CAP. Since CAP cannot anticipate or control the conditions under which this information and its product may be used, each user should review the information in the specific context of the intended application. CAP will not be responsible for damages of any nature resulting from the use of or reliance upon the information.

This technical datasheet is effective as from **July 2016** and supersedes all data previously published.

### PT. Chandra Asri Petrochemical, Tbk.

#### Site Office:

Jl. Raya Anyer Km. 123, Ciwandan, Cilegon,  
Banten 42447, Indonesia  
P: +62 254 601501, F +62 254 601505  
E: GROUPEPRND@capcx.com

#### Head Office:

Wisma Barito Pacific Tower B, 2<sup>nd</sup> Floor  
Jl. Let. Jend. S. Parman Kav. 62-63  
Jakarta 11410, Indonesia  
P: +62 21 5307950, F +62 21 5308930  
[www.chandra-asri.com](http://www.chandra-asri.com)



Responsible Care®

