QINGDAO HAIWAN CHEMICAL CO.,LTD.

NO. 66 GANGFENG ROAD, POLI TOWN, HUANGDAO DISTRICT, QINGDAO, CHINA

Tel:86-532-67716668

POLYVINYL CHLORIDE RESIN HS-1000R

Properties: Features thermo plasticity, being insoluble into water, gasoline and alcohol, swelled or dissolved into ether, ketone, chlorinated aliphatic hydrocarbons, and aromatic hydrocarbon, high resistance to corrosion, and good dielectric property.

Packaging and storage:25kgs bag and 1150kgs Jumbo bag. Don't store it in the open air. Avoid in the direct sunlight and keep dry.

TECHNICAL PROPERTY

| ITEMS | | Spec. |
|--------------------------------------|---------|---------|
| Viscosity(ml/g) | | 107-118 |
| K value | | 66-68 |
| Impurity particle number | | 16max |
| Volatiles (incl. water), % | | 0.40max |
| Bulk density, g/ml | | 0.53min |
| Sieve ratio% | 0.25mm | 1.6max |
| | 0.063mm | 97min |
| "fish eye" number unit /400cm2 | | 20max |
| 100g resin plasticizer absorbtion, g | | 20min |
| Whiteness(after 160°C10min) | | 80min |
| Residual VCM, ppm | | 1.0max |

There are slightly variations possible with regard to the above mentioned property data, however, which have no influence on the described application properties.

^{***}this data is general properies of this product so it is not availabl e for preparation of specification***