

Product Data Sheet

PT. Lotte Chemical Titan Nusantara. (Formerly known as PT TITAN Petrokimia Nusantara) Head Office: Mangkuluhur City Tower One, 32nd Floor, Jl. Jendral Gatot Subroto Kav. 1-3, Karet Semanggi, Setiabudi, Jakarta Selatan - 12930, Indonesia Phone: +62 21 27883355 Fax: +62 21 27883366/99 Site Location: Jl. Raya Merak Km.116 Cilegon 42436, Banten Indonesia Phone +62 254 571333 Fax: +62 254 571290 Email: tsc@lottechem.co.id Website: www.lottechem.co.id

Titanvene™ HD5609AA

Tape and Monofilament Applications

Titanvene™ **HD5609AA** is a high density polyethylene suitable for extrusion and stretching process for filaments and tapes. Titanvene™ **HD5609AA** is characterised by its low gel content, stretching with few breaks and high tenacity.

Applications

Titanvene™ **HD5609AA** is designed for:

- Tarpaulin covers

- Mosquito nets and fishing nets. - Woven tapes.

Recommended Processing Conditions (1)

Titanvene™ HD5609AA can be easily processed on normal polyethylene monofilament machines at temperatures in the range of 220°C to 265°C.

Food Contact Compliance

Titanvene™ **HD5609AA** can be used in food contact applications. Please contact your nearest PT. Lotte Chemical Titan Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value (2)	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	0.9	g/10 min	ISO 1133 Condition 4
Nominal Density	0.954	g/cm³	ISO 1183 Method D
Vicat Softening Point	127	°C	ISO 306
Melting Point	131	°C	ISO 3146 Method C
Mark	V-1 (2) (4)	l lm!s	To at Mathead
Mechanical Properties (3)	Value (2) (4)	Unit	Test Method
Tensile Stress at Yield	27	MPa	
•			ISO/R 527 Type 2 Speed C
Tensile Stress at Yield	27	MPa	ISO/R 527 Type 2 Speed C
Tensile Stress at Yield Elongation at Break	27 1700	MPa %	ISO/R 527 Type 2 Speed C ISO/R 527 Type 2 Speed C

The optimum processing conditions can be different from one machine to the others, depend on the mould and part design. The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.

"World's 1st Halal Certified Resins - preserve integrity, wholesomeness & hygiene "

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

DEV-4-REC-1619-06 Dec 20

Measured on compression molded plaques. Environment Stress Cracking Resistance 10% Igepal : CO-630